

# DICOPLAN

## Technical sheet

### USES

Recommended use Flexible doors, Tarpaulins for agriculture, Covers and lagging, Truck Tarpaulins, Truck roofing

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

### GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den							
Coating	PVC Lowick coating both side							
Finish	Cleangard lacquer both sides							
Weight	680					g/m <sup>2</sup>	ISO 3801	
Width	150	250	250	250	300	300	cm	
Roll length	60	30	60	250	30	60	ml	

### FABRIC RESISTANCE

Tensile strength	260	250	daN/5cm	NF EN ISO 1421
Tear strength	32	28	daN	DIN 53.363
Adhesion	10		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.

SYSTEM  
LOWICK

FINITION  
CLEANGARD



RESOURCE

REACH  
COMPLIANCE

MADE IN  
FRANCE



**DICKSON COATINGS**  
415, avenue de Savoie  
F-38110 Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01  
[www.dickson-coatings.com](http://www.dickson-coatings.com)



GLEN RAVEN™

Glen Raven™ is a trademark  
and Dickson® is a registered  
trademark of Glen Raven, Inc.